# AIRDUC® PUR 356 EC (XHD)
















# Electrically conductive polyurethane hose, super-heavy duty

#### **Application**

- hose/ ducting for high throughput of extremely abrasive bulk material, granulate and stone
- vacuum truck, suction vehicle, dry suction truck: industrial cleaning, furnace cleaning
- explosion hazard area
- Coal mine, mine, tunnelling: ventilation, methane extraction
- · raw material conveying hose for powders, granulates, sand, quartz, gravel, shards and chips/ shavings
- silo, silo vehicle/ silo truck, tanker/ tank truck: silo charging, silo discharging

#### **Properties**

- super-heavy duty
- extremely abrasion-resistant with reinforcement underneath wire and narrow hose pitch

- good resistance to oil, gasoline, and chemicals
- · very good low temperature flexibility
- · electrically conductive wall: electrical and surface resistance  $<10^3\Omega$  (according to NFPA  $652 < 10^{6}\Omega$ )
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: pneumatic transport of flammable dusts and bulk materials (Zone 20, 21, 22 inside), aspiration of combustible dusts (Zone 22 inside),
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: for conveying for flammable liquids (inside zone 0, 1, 2), for conveying for non-flammable liquids, for use in zone 1 and 2 (gases), for use in zone 0 (gases)
- according to DIN 26057 Type 4
- · conforms to RoHS guideline
- REACH according to --> Technology / Technical Information / REACH

### Temperature range

• -40°F to 195°F

#### Design

- AIRDUC<sup>®</sup> profile hose
- · spring steel wire firmly embedded in wall
- wall: electrically conductive premium esterpolyurethane (Pre-PUR®)
- wall thickness 0.08 to 0.10 in approx.
- · reinforcement of the primary abrasion areas

#### **Delivery variants**

- further diameters and lengths available on request
- black (standard)
- · customer-specific branding

I.D.	outer Ø	Pressure	Vacuum	Bending radius	Weight	Dimensions in Stock	Order No.	Production lengths
(in / mm)	(in)	(psi)	(inHG)	(in)	(lb/ft)	(ft)		(ft)
1,5 / 38	1.929	55.260	29.530	4.094	0.531	10 15	356-0038-1003	-
- / 40	2.008	52.722	29.530	4.291	0.551	10 15	356-0040-1003	-
- / 50	2.402	42.787	29.530	5.276	0.672	10 15	356-0050-1003	-
2 / 50-51	2.441	40.611	29.530	5.276	0.679	10 15	356-0051-1003	-
2,36 / 60	2.795	36.042	29.530	6.142	0.793	10 15	356-0060-1003	-
2,5 / 63-65	2.913	34.737	29.530	6.417	0.833	10 15	356-0063-1003	-
- / 65	2.992	33.432	29.530	6.654	0.853	10 15	356-0065-1003	-
- / 70	3.228	31.111	29.530	7.323	0.921	10 15	356-0070-1003	-
- / 75	3.425	29.153	29.530	7.677	0.981	10 15	356-0075-1003	-
3 / 76	3.465	28.935	29.530	7.677	0.995	10 15	356-0076-1003	-
-/80	3.622	27.413	29.530	8.071	1.042	10 15	356-0080-1003	-
-/100	4.449	24.439	29.530	10.709	1.526	10 15	356-0100-1003	-
4 / 102	4.528	24.004	29.530	10.709	1.552	10 15	356-0102-1003	-

Positive and negative pressure ratings are the recommended maximum operating values. Products can be manufactured to meet higher operating values upon request. The bend radius is calculated from the center of the hose in an arched position. Additional information at <a href="https://www.norres.com/us/technology/">www.norres.com/us/technology/</a>. NORRES reserves the right to modify technical data at any time. Technical data based on tests at 68°F and are approx. values. Proper use and maintenance of NORRES hoses is the sole responsibility of purchaser and ultimate user of the product. The individual conditions, applications and the number of variables make firm recommendations technically impossible. This information is intended as a general guide only.

Positive and negative pressure ratings are the recommended maximum operating values. Products can be manufactured to meet higher operating values upon request. The bend radius is calculated from the center of the hose in an arched position. Additional information at www.norres.com/us/technology/. NORRES reserves the right to modify technical data at any time. Technical data based on tests at 68 °F and are approx. values. Proper use and maintenance of NORRES hoses is the sole responsibility of purchaser and ultimate user of the groduct. The individual conditions, applications and the number of variables make firm recommendations technically impossible. This information is intended as a general guide only.

# AIRDUC® PUR 356 EC (XHD)











## Accessories



**CONNECT 243** 



CONNECT THREAD CONNECT 240 EC FITTING 234





CONNECT SAFETY **CLAMP ASSEMBLY** 



**CONNECT 246 AS** 



**CONNECT 245** 



CONNECT 240 + 241 CONNECT PRESS



**ASSEMBLY 232** 



CONNECT MOULD **ASSEMBLY 233** 



CLAMP 211



**CONNECT 244** 



CLAMP 216



**CONNECT 228** 



**CONNECT 242**